



NB Bagnara

Selection



True stones



Amiamo tutte le nostre pietre, ma alcune di queste ci ispirano di più. In questo catalogo vorremmo presentare la nostra selezione di materiali unici, che rispecchiano la bellezza di tutto il mondo. Grazie all'estrazione nelle nostre cave di proprietà o nelle cave partner, possiamo garantire una fornitura costante e un'ottima qualità.

Wir lieben all unsere Natursteine, aber einige davon inspirieren uns besonders. In diesem Katalog präsentieren wir unsere Selektion an Materialien – einzigartige Steine, die die Schönheit der ganzen Welt widerspiegeln. Durch den Abbau in unseren eigenen Steinbrüchen oder Partnerbrüchen können wir ein solides Vorkommen und beste Qualität garantieren.

We love all our natural stones. However, some of them particularly inspire us. In this catalogue we would like to present our selection of unique stones, which are reflecting the beauty of the world. Thanks to the extraction of the materials in our own quarries and partner-quarries, we are able to guarantee a constant supply and high quality.



Menara Astra, Jakarta

SILVER CLOUD

timeless and versatile

Come il suo nome lascia trasparire, il granito americano Silver Cloud richiama l'idea di una nuvola argentata. Il colore di base chiaro e la struttura movimentata di color grigio argento a seconda del tipo di taglio diventa nuvolata o longitudinale. La sua struttura e il suo colore rendono questo materiale un prodotto particolare e senza tempo. Grazie alle sue ottime caratteristiche tecniche, questa pietra compatta si adatta a vari utilizzi sia per interni che per esterni. Inoltre, grazie alla sua resistenza all'acido e alla sua durezza, il Silver Cloud è ideale anche come piano di lavoro in cucina. Il colore di base uniforme e l'impercettibile differenza in colore e struttura rinvenibile da blocco a blocco, rendono ideale l'uso del materiale su vaste superfici, come ad esempio su facciate e pavimenti.

Wie sein Name bereits andeutet, erinnert der amerikanische Granit Silver Cloud an eine silberne Wolke. Der helle Grundton und die silbergrauen, stark bewegten Aderungen des Granits erscheinen je nach Schneiderichtung gewolkt oder längs fließend. Seine Struktur und Farbe lässt das Material anregend und zeitlos wirken. Dank seiner hervorragenden technischen Eigenschaften eignet sich das Hartgestein für vielfältige Anwendungen im Innen- und Außenbereich. Aufgrund seiner Säurebeständigkeit und Härte ist Silver Cloud auch ideal als Küchenarbeitsplatte. Der konstante Grundton und der unmerkliche Farb- und Strukturunterschied von Block zu Block erlaubt zudem den idealen Einsatz des Materials für großflächige Anwendungen wie beispielsweise Fassaden und Böden.

As its name suggests, the American Silver Cloud granite is reminiscent of a silver cloud. The bright base tone and the silvery, strongly dynamic veins of the granite appear, depending on the cutting direction, clouded or longitudinally flowing. Its structure and colour make the material stimulating and timeless. Thanks to its excellent technical properties, this hard stone is suitable for a wide range of indoor and outdoor applications. Because of its acid resistance and hardness, Silver Cloud is also ideal as a kitchen worktop. The constant base tone and the imperceptible colour and structure difference from block to block also allows the ideal use of the material for large-area applications such as facades and floors.

www.silvercloudquarry.com

References

Amari Hotel, *Doha, Qatar*
Arcapita Bank, *Manama, Bahrain*
Casino Montecampione, *Italy*
Chongqing Rural Commercial Bank, *China*
Complexe Jules Dallair, *Quebec City, Canada*
Four Seasons Hotel, *London, GB*
La Desence Plaza, *Paris, France*
Marina Tower, *Beiruth, Lebanon*
Menara Astra, *Jakarta, Indonesia*
Salesforce Tower, *Chicago, USA*

Metropolitan, *Warsaw, Poland*
Oxford College of Emory university, *Atlanta, USA*
Sinsa Square, *Seoul, South Korea*
Sky Tower, *Milan, Italy*
The Address Boulevard, *Dubai, UAE*
The Address Hotel, *Dubai, UAE*
Two Union Square, *Seattle, USA*
University of Georgia, *Atlanta, USA*
The Fawkner, *Melbourne, Australia*



Marmomac 2021, Verona

Technical details Silver Cloud*

type of rock	Migmatic Granite		
quarry location	USA	www.silvercloudquarry.com	
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2631–2640 kg/m ³	164–165 lb/ft ³
compressive strength	UNI EN 1926	147 MPa	21321 psi
flexural strength	UNI EN 12372 UNI EN 13161	8,4 MPa	1218 psi
moisture absorption	UNI EN 13755	0,3%	0.3%
abrasion resistance	UNI EN 14157	19,96 mm→16,3 mm	0.79 in→0.64 in

*The above data is indicative and without guarantee. Detailed test results on request.
 **All values in this column are based on European test norms and converted into the equivalent imperial units.



Sinsa Square, South Korea



Silver Cloud
polished





NERO ASSOLUTO ZIMBABWE

timeless and profound

Uno sguardo al nero profondo del cielo notturno descrive l'eleganza senza tempo del granito africano. Ed è proprio l'inusitata profondità del suo colore a simboleggiare quello che viene definito il "nero assoluto". Il Nero Assoluto Zimbabwe è disponibile in diverse grane: da una struttura molto fine e particolarmente scura, fino a una struttura mediamente fina e più chiara. Per ogni progetto si può individuare la giusta categoria di prezzo e qualità, e ciò rende il materiale ampiamente versatile. Il carattere del Nero Assoluto Zimbabwe è profondo, misterioso, senza tempo e moderno, adattandosi praticamente a ogni ambiente senza alcun limite.

Ein Blick zum tiefschwarzen Nachthimmel beschreibt die zeitlose Eleganz des afrikanischen Granits. Unerreicht in seiner Farbtiefe ist er das Sinnbild für absolutes Schwarz. Nero Assoluto Zimbabwe ist in unterschiedlichen Körnungen verfügbar: von feinkörnig und besonders dunkel bis mittelkörnig und etwas heller. So findet man für jede Projektidee je nach Bedarf die passende Qualitäts- und Preiskategorie, wodurch das Material einen besonders breit gefächerten Anwendungsbereich findet. Der Charakter des Nero Assoluto Zimbabwe ist tiefgründig, geheimnisvoll, zeitlos und modern und kann sich in nahezu jedes Ambiente nahtlos einfügen.

A glance at the deep black night sky describes the timeless elegance of this African granite. Unrivalled in its color depth, it is the symbol of absolute black. Nero Assoluto Zimbabwe is available in different grain sizes: from fine grained and especially dark to medium grained and slightly lighter. The appropriate quality and price category for every project idea can be found, making the material appropriate for a particularly wide range of applications. The character of the Nero Assoluto Zimbabwe is profound, mysterious, timeless and modern, and it can be seamlessly integrated into almost any environment.

www.crgquarries.com

References

Tour Odeon, *Monaco, Monte Carlo*
Macedonian Philharmonic Orchestra, *Skopje, Macedonia*
John Hancock Center Lobby Week, *Chicago, USA*
101 Collins, *Melbourne, Australia*



floor, polished

Technical details Nero Assoluto Zimbabwe*

type of rock	Granite (Gabbro)		
quarry location	Zimbabwe	www.neroassolutozimbabwe.com	
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	3066–3078 kg/m³	191–192 lb/ft³
compressive strength	UNI EN 1926	270 MPa	39160 psi
flexural strength	UNI EN 12372 UNI EN 13161	34,8 MPa	5047 psi
moisture absorption	UNI EN 13755	0,1%	0.1%
abrasion resistance	UNI EN 14157	19,96 mm→15,9 mm	0.79 in→0.63 in


*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



wall, rigato


Nero Assoluto Zimbabwe
polished




slab




flamed & brushed




honed



satin



waterjet



sandblasted



BROWN SILK

linear and unique



floor, satin




Alchemist, Copenhagen, Denmark

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal & partially external		
acid resistance	partially		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2725–2734 kg/m ³	170–171 lb/ft ³
compressive strength	UNI EN 1926	75,92 MPa	11011 psi
flexural strength	UNI EN 12372 UNI EN 13161	14,4 MPa	2089 psi
moisture absorption	UNI EN 13755	0,1%	0.1%
abrasion resistance	UNI EN 14157	20,5 mm→19,0 mm	0.81 in→0.75 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Brown Silk
polished



slab



waterjet & brushed



honed



satin



sandblasted



PANNONIA GRÜN

rustic and modern



floor, satin




kitchen, satin

Technical details*


type of rock	Chlorite Schist		
quarry location	Austria		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	3050–3109 kg/m ³	190–194 lb/ft ³
compressive strength	UNI EN 1926	162,4 MPa	23554 psi
flexural strength	UNI EN 12372 UNI EN 13161	22,9 MPa	3321 psi
moisture absorption	UNI EN 13755	0,32%	0.32%
abrasion resistance	UNI EN 14157	19,10 mm	0.75 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Pannonia Grün
polished, CC





MYSTIC GREY

wild and mysterious



kitchen, satin



floor, satin




Technical details*

type of rock	Granite (Diorite)		
quarry location	Brazil		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2868–2934 kg/m ³	179–183 lb/ft ³
compressive strength	UNI EN 1926	212 MPa	30748 psi
flexural strength	UNI EN 12372 UNI EN 13161	22,7 MPa	3292 psi
moisture absorption	UNI EN 13755	0,3%	0.3%
abrasion resistance	UNI EN 14157	19,52 mm→18,8 mm	0.77 in→0.74 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.

Mystic Grey
polished





AZUL ARAN®

refreshing and exclusive

Il prezioso granito spagnolo Azul Aran dà una sensazione di freschezza ed esclusività grazie ai suoi feldspati grigio-blu e alle ombreggiature bianche. La sua struttura è unica al mondo: grazie alla sua superficie dall'aspetto mosso ogni lastra è irripetibile, come una creazione artistica naturale. Il suo carattere è aggraziato, delicato ed elegante. Grazie alla sua resistenza agli acidi, il materiale funge bene da piano di lavoro in cucina e si presta a numerosi altri utilizzi per gli ambienti interni.

Der hochwertige spanische Granit Azul Aran wirkt durch seine blau-grauen Feldspate und weißen Schattierungen erfrischend und exklusiv. Seine Struktur ist weltweit einzigartig. Durch seine bewegte Struktur ist jede Platte des Materials individuell, wie ein Kunstwerk der Natur. Sein Charakter ist lieblich, zart und edel. Dank seiner Säurebeständigkeit eignet sich das Material unter anderem auch sehr gut für Küchenarbeitsplatten und viele andere Anwendungen im Innenbereich.

The high-quality Spanish Azul Aran granite is refreshing and exclusive due to its blue-grey feldspar and white shading. Its structure is unique in the world. Because of its dynamic structure, each slab of the material is different, like a piece of artwork made by Nature. Its character is lovely, delicate and noble. Due to its acid resistance, the material is also suitable for kitchen worktops and many other indoor applications.

www.azularan.com

References

Business Town, *Kuwait City, Kuwait*
Clinica Ars Medica, *Gravesano, Switzerland*
Conrad Hotel, *Riad, Saudi Arabia*
El Corte Ingles, *Madrid, Spain*
Eleven Times Square, *New York, USA*
Four Little Houses, *Seoul, South Korea*
Hyatt Regency, *Chicago, USA*
Ministry of Education, *Kuwait City, Kuwait*
Sansi Pedralbes Hotel, *Barcelona, Spain*
Urbis Residential, *Spain*



Hyatt Regency Hotel, Chicago



kitchen, satin

Technical details Azul Aran^{®*}

type of rock	Migmatic Granite		
quarry location	Spain	www.azularan.com	
application area	internal & partially external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2619–2639 kg/m³	163–165 lb/ft³
compressive strength	UNI EN 1926	123 MPa	17840 psi
flexural strength	UNI EN 12372 UNI EN 13161	14,2 MPa	2060 psi
moisture absorption	UNI EN 13755	0,2%	0.2%
abrasion resistance	UNI EN 14157	19,96 mm→14,5 mm	0.79 in→0.57 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.




Eleven Times Square, NY City



Azul Aran®
polished



slab



honed



satin



waterjet & brushed



waterjet



sandblasted



CARBON GREY
contemporary and unobtrusive



kitchen, satin



floor, satin

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	norm #	metric units**	imperial units
apparent density	NBR 12766	2806–2871 kg/m ³	175–179 lb/ft ³
compressive strength		42,2 MPa	6121 psi
flexural strength	NBR 12763 NBR 12767	6,7 MPa	972 psi
moisture absorption	NBR 12766	0,41%	0.41%

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on Brazilian test norms and converted into the equivalent metric units.


Carbon Grey
polished



slab



honed



satin



sandwaterjet & brushed



ATLANTIC STONE
hard and natural



bathroom, polished



kitchen, polished

Technical details*

type of rock	Granite (Rhyolite)		
quarry location	China		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2590–2620 kg/m ³	162–164 lb/ft ³
compressive strength	UNI EN 1926	234,6 MPa	34026 psi
flexural strength	UNI EN 12372 UNI EN 13161	33,5 MPa	4859 psi
moisture absorption	UNI EN 13755	0,5%	0.5%
abrasion resistance	UNI EN 14157	16 mm	0.63 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.




Atlantic Stone
polished



slab



satin



honed



sandwaterjet



BEOLA NERA
natural and timeless



Kitchen Eggersmann, satin




bathroom,satin

Technical details*

type of rock	Gneiss
quarry location	Italy
application area	internal & external
acid resistance	yes
frost resistance	yes


*The above data is indicative and without guarantee. Detailed test results on request.



Beola Nera
polished



slab



satin



sandwaterjet



sandblasted



MOONROCK
soft and natural



bathroom, sandwaterjet & brushed



kitchen, studio Archi Katy, honed

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal & partially external		
acid resistance	partially		
frost resistance	yes		
	EN norm #	metric units	imperial**
apparent density	UNI EN 1936	2725–2734 kg/m ³	170–171lb/ft ³
compressive strength	UNI EN 1926	75,92 MPa	11011 psi
flexural strength	UNI EN 12372 UNI EN 13161	14,4 MPa	2089 psi
moisture absorption	UNI EN 13755	0,1%	0.1%
abrasion resistance	UNI EN 14157	20,5 mm→19,0 mm	0.81 in→0.75 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Moonrock
polished



slab



honed




satin



sandwaterjet



sandwaterjet & brushed



ALPS GLITTER

high-grade and rustic



Hotel Stroblhof, Italy

Technical details*


type of rock	Mica Schist		
quarry location	Italy		
application area	internal & partially external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial untis**
apparent density	UNI EN 1936	2840–2900 kg/m ³	177–181 lb/ft ³
flexural strength	UNI EN 12372 UNI EN 13161	8,5 MPa	1233 psi
moisture absorption	UNI EN 13755	0,25%	0.25%
abrasion resistance	UNI EN 14157	20,5 mm→15,8 mm	0.81 in→0.62 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Alps Glitter
polished





BLACK PEPPER

fresh and smart



kitchen, satin



kitchen, polished

Technical details*




type of rock	Granite (Diorite)		
quarry location	Turkey		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	3004-3024 kg/m ³	188-189 lb/ft ³
compressive strength	UNI EN 1926	206 MPa	29878 psi
flexural strength	UNI EN 12372 UNI EN 13161	21,3 MPa	3089 psi
moisture absorption	UNI EN 13755	0,2%	0.2%
abrasion resistance	UNI EN 14157	19,5 mm → 17,3 mm	0.77 in → 0.68in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Black Pepper
polished





PORTLAND TAUPE
soft and versatile



wall cladding, VC



floor, sandwaterjet & brushed, CC

Technical details*

type of rock	Limestone		
quarry location	USA		
application area	internal & partly external		
acid resistance	yes		
frost resistance	partial		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2640 kg/m ³	164,80 lb/ft ³
compressive strength	UNI EN 1926	59 MPa	8557,23 psi
flexural strength	UNI EN 12372 UNI EN 13161	10,9 MPa	1580,91 psi
moisture absorption	UNI EN 13755	0,5 %	0.5%
abrasion resistance	UNI EN 14157	24,3 mm	0.95 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.

A close-up photograph of a textured, brownish-grey surface, likely a stone or concrete slab. A prominent horizontal line runs across the middle of the frame, possibly a joint or a crack. The texture is granular and uneven, with various shades of taupe and brown.

Portland Taupe VC
polished

A close-up photograph of a textured, brownish-grey surface, similar to the one above. A diagonal line runs from the bottom left towards the center. The texture is granular and uneven, with various shades of taupe and brown.


Portland Taupe CC
polished



slab, VC



honed, VC



sandblasted, VC



honed, CC



sandblasted, CC



slab, CC



BETHEL WHITE

gentle and calming



ADNOC HQ, Abu Dhabi



Qatar National Convention Center, Doha

Technical details*

type of rock	Granite		
quarry location	USA		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2631 - 2632 kg/m ³	164 lb/ft ³
compressive strength	UNI EN 1926	183 MPa	26542 psi
flexural strength	UNI EN 12372 UNI EN 13161	11 MPa	1595 psi
moisture absorption	UNI EN 13755	0,3%	0.3%
abrasion resistance	UNI EN 14157	15,7 mm	0.62 in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.


Bethel White
polished



slab



flamed



sandblasted



waterjet



KUROCA
natural and beautiful



fireplace and staircase, satin



kitchen, polished

Technical details*

type of rock	Quartzite		
quarry location	Angola		
application area	internal & partially external		
acid resistance	yes		
frost resistance	limited		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2730 kg/m ³	170,42 lb/ft ³
flexural strength	UNI EN 12372 UNI EN 13161	26,6 MPa	3858 psi
moisture absorption	UNI EN 13755	0,1%	0.1%
abrasion resistance	UNI EN 14157	16 mm	0.62 in

*The above data is indicative and without guarantee. Detailed test results on request.


**All values in this column are based on European test norms and converted into the equivalent imperial units.




Kuroca
polished



slab



satin



corteccia & rigato



VERDE LAPPONIA
wild and untamed



Kitchen top, polished




Living room, polished

Technical details*

type of rock	Quartzite		
quarry location	Norway		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2920 kg/m ³	182 lb/ft ³
compressive strength	UNI EN 1926	212 MPa	30748 psi
flexural strength	UNI EN 12372 UNI EN 13161	22,9 MPa	3321 psi
moisture absorption	UNI EN 13755	0,09%	0.09%
abrasion resistance	UNI EN 14157	19 mm	0.75 in

*The above data is indicative and without guarantee. Detailed test results on request.


**All values in this column are based on European test norms and converted into the equivalent imperial units.



Verde Lapponia
polished



slab



honed



satin



BLACK TEMPEST

elegant and modern



table, honed



shower, honed

Technical details*



type of rock	Quartzite				
quarry location	Brazil				
application area	internal & partly external				
acid resistance	yes				
frost resistance	yes				
	EN norm #	metric units		imperial units**	
apparent density	UNI EN 1936	2659 kg/m³		544,60	lb/ft³
compressive strength	UNI EN 1926	114	MPa	16534,3	psi
flexural strength	UNI EN 12372 UNI EN 13161	14,7	MPa	1015,2	psi
moisture absorption	UNI EN 13755	0,2	%	0,2	%
abrasion resistance	UNI EN 14157	16,3	mm	0,641	in

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Black Tempest
polished





TERRA MATER
noble and striking



shower, honed



kitchen, ©Steininger, satin

Technical details*

type of rock	Marble
quarry location	Turkey
application area	internal
acid resistance	no
frost resistance	no

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Terra Mater
polished





QUARZITE TIFFANY
elegant and exclusive



Technical details*

type of rock	Quartzite				
quarry location	Brazil				
application area	internal & partly external				
acid resistance	yes				
frost resistance	yes				
	EN norm #	metric units		imperial units**	
apparent density	UNI EN 1936	2653	kg/m ³	165,62	lb/ft ³
compressive strength	UNI EN 1926	148,30	MPa	21509,09	psi
flexural strength	UNI EN 12372 UNI EN 13161	18,21	MPa	2641,13	psi
moisture absorption	UNI EN 13755	0,14	%	0,14	%

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Quarzite Tiffany
polished



slab



honed



satin



BRECHE DE AUBISQUE

elegant and unique




Technical details*


type of rock	Marble		
quarry location	France		
application area	internal & partly external		
acid resistance	no		
frost resistance	partly		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2700 kg/m ³	168,55 lb/ft ³
compressive strength	UNI EN 1926	235 Mpa	34083,9 psi
flexural strength	UNI EN 12372 UNI EN 13161	13,2 Mpa	1914,4 psi
moisture absorption	UNI EN 13755	0,15 %	0,15 %
abrasion resistance	UNI EN 14157	22 mm	0,86 in

*The above data is indicative and without guarantee. Detailed test results on request.


**All values in this column are based on European test norms and converted into the equivalent imperial units.




Breche De Aubisque
polished



slab



polished



polished



slab



SEPHORA
gorgeous and sophisticated



Technical details*

type of rock	Quartzite
quarry location	Brazil
application area	internal
acid resistance	yes
frost resistance	partly

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Sephora
polished



slab



Honed



satin



QUARZITE EBANO
refined and enchanting



Bathroom, honed



shower, honed

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal		
acid resistance	yes		
frost resistance	partly		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2629 kg/m ³	168,55 lb/ft ³
compressive strength	UNI EN 1926	115 Mpa	16679,3 psi
flexural strength	UNI EN 12372 UNI EN 13161	16,6 - 20,4 Mpa	2407,6 - 2958,7 psi
moisture absorption	UNI EN 13755	0,2 %	0,2 %

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.




Quarzite Ebano
polished



slab VC



satin VC



satin CC



slab CC



MADREPERLA
warm and beautiful



living, honed

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2660 kg/m ³	166,05 lb/ft ³
compressive strength	UNI EN 1926	94,6 Mpa	13720,57 psi
flexural strength	UNI EN 12372 UNI EN 13161	10,26 Mpa	1488,08 psi
moisture absorption	UNI EN 13755	0,29 %	0,29 %

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



Madreperla
polished



slab



polished



honed



slab



NOIR AUBISQUE

warm and beautiful



slab, polished

Technical details*

type of rock	Marble
quarry location	France
application area	internal
acid resistance	no
frost resistance	partly

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.



GREEN GALAXY

warm and beautiful



slab, polished

Technical details*

type of rock	Quartzite		
quarry location	Brazil		
application area	internal & external		
acid resistance	yes		
frost resistance	yes		
	EN norm #	metric units	imperial units**
apparent density	UNI EN 1936	2685 kg/m ³	167,61 lb/ft ³
compressive strength	UNI EN 1926	122,1 Mpa	17709,10 psi
flexural strength	UNI EN 12372 UNI EN 13161	24,1 Mpa	3495,40 psi
moisture absorption	UNI EN 13755	0,15 %	0,15 %

*The above data is indicative and without guarantee. Detailed test results on request.

**All values in this column are based on European test norms and converted into the equivalent imperial units.

Bagnara worldwide



Corporate headquarters

Nikolaus Bagnara S.p.A.

Italy - 39057 Appiano (BZ)
Via Madonna del Riposo, 34
T +39 0471 66 21 09
F +39 0471 66 47 04
info@bagnara.net

Slab storage facilities & factory

Italy - 37010 Cavaion Veronese (VR)
Viale Enrico Fermi, 8
T +39 045 626 91 82
F +39 045 723 80 99
cavaion@bagnara.net

Slab storage facilities

Italy - 37020 Volargne (VR)
Via del Marmo, 655/B
T +39 045 686 00 59
F +39 045 686 09 45
volargne@bagnara.net

Block storage facilities

Italy - 37010 Rivoli Veronese (VR)
Via dell'Ecologia, 1
T +39 045 626 90 94
F +39 045 626 13 26
rivoli@bagnara.net

Block storage facilities

Italy - 54100 Massa Carrara (MS)
Via Massa Avenza, 249
T +39 0585 5 48 45
F +39 0585 50 42 60
carrara@bagnara.net

www.bagnara.net

■ Quarries

CRG Quarries (PVT) Ltd

Zimbabwe - Harare
11 Bertram Road
T +263 477 84 64
info@crgquarries.com

www.crgquarries.com

Broad River Quarries Llc

Quarry & offices

USA - Lithonia, GA 30058
7340 Scales Rd
T +1 (404) 395 09 36
info@brq.us

Mail address:
PO BOX 1200, Redan, GA, 30074

www.silvercloudquarry.com

Azul Aran

Legal office

Spain - 25530 Vielha (Lleida)
Avda. Castiero, 17 entlo.

Quarry & offices

Spain - 25540 Les (Lleida)
T +34 973 64 73 95
F +34 973 64 72 07
info@azularan.com

www.azularan.com





○ Distribution facilities

Shin Bagnara Co. Ltd

Korea - Gyeonggi-do 12790
663-33 Opo-ro, Opo-eup,
Gwangju-si
T +82 (0)31 769 57 70
F +82 (0)31 769 89 31

● Representative offices

Scandinavia

Turku - Finland

East Europe

Belgrade - Serbia

South East Asia & Oceania

Sydney - Australia

South America

Vitória - Brazil

India

Bangalore - India

Ukraine

Zhytomyr - Ukraine

**SLABCO International
Marble & Granite Inc**

Distribution Georgia

USA - Elberton, Georgia 30635
1821 Lexington Hwy
T +1 (706) 213 12 55
F +1 (706) 213 12 51

www.slabcomg.com

Distribution South Carolina

USA - Travelers Rest, SC 29690
925 North Hwy. 25
T +1 (864) 834 12 58

www.slabcomgsc.com



www.bagnara.net

